

artu



Fabric sample book

artu


C1	Gemma	3
	Lars	4
	Rino	5
	Today	6
C2	Letto	7
	Now or never	8
	Presence	9
	Run again	10
	Tender way	11
C3	Concentration	12
	Good morning	13
	Good morning P	14
	Good night	15
	One moment	16

Table of content

artu

Gemma

Uphlostery grade – C1



Grammage m²

340g/m² +/-5%

Composition

88%PES 9%RA 3%NY

Usable width

min 140cm

Martindale Test

60000-70000

Thread displacement

1,5-1,7 mm WARP / 1,2-1,4 mm WEFT

Tendency to pilling and peeling

4

Fastness to rubbing dry


light-5 / medium-4-5 / dark-4-5

Fastness to rubbing wet


light-5 / medium-5 / dark-4-5



01



04



06




10




11




13



39



58



59




60




61




63




70




72



75



77



79



85



86



90



93




97

artu

Lars

Uphlostery grade – C1



Grammage m²

240g/m² +/-5%

Composition

100% Polyester

Usable width

min. 140cm

Martindale Test

80000-90000

Thread displacement

3,6-4,0 mm WARP / 3,4-3,8 mm WEFT

Tendency to pilling and peeling

4

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5



07




27



35



45



59



62



68




73




74




75




76



77



79



81



82



87



88



89




90



92




96




97



98



99




100

artu

Rino

Uphlostery grade – C1



Grammage m²

210g/m² +/-5%

Composition

100% Polyester

Usable width

min. 140cm

Martindale Test

60000-70000

Thread displacement

1.9-2.1 mm WARP / 1.9-2.1 mm WEFT

Tendency to pilling and peeling

4

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5



03



06




09



11



16




29



31



32




37



58




59



61




63




70




73



75



77



79



80




84



87




88



93



94



97

artu

Today

Uphlostery grade – C1

Grammage m²	450g/m ² +/-5%
Composition	100% Polyester
Usable width	min. 140cm
Martindale Test	60000-100000
Thread displacement	1,7-1,9 mm WARP / 1,9-2,1 mm WEFT
Tendency to pilling and peeling	4-5
Fastness to rubbing dry	4-5
Fastness to rubbing wet	4-5



03




13



15



18



24



34



38




55



64




66




67



70




72



75



78



80



85



93



98

artu

Letto

Uphlostery grade – C2

Grammage m²

380g/m² +/-5%

Composition

100% Polyester

Usable width

min. 140cm

Martindale Test

90 000->100 000 T

Thread displacement

2,0-2,2 mm WARP / 2,1-2,3 mm WEFT

Tendency to pilling and peeling

4

Fastness to rubbing dry

light-4-5 / medium-4-5 / dark-4-5

Fastness to rubbing wet

light-4-5 / medium-4-5 / dark-4-5



**PET
FRIENDLY**



**EASY
CLEAN**



03



11



38




39



49




56




60




61




69




73




75




77




79




80




83




85




87




88




92



93



97



99

artu

Now or never

Uphlostery grade – C2



RECYCLED
POLYESTER

Grammage m²

420g/m² +/-5%

Composition

100% rPES

Usable width

min. 140cm

Martindale Test

90 000->100 000

Thread displacement

0,5-0,7 mm WARP / 1,1-1,3 mm WEFT

Tendency to pilling and peeling


3-4

Fastness to rubbing dry


light-5 / medium-4-5 / dark-4-5

Fastness to rubbing wet

light-4-5 / medium-5 / dark-4-5




01



03



06



16



83



92

artu

Presence

Uphlostery grade – C2

Grammage m²

540g/m² +/-5%

Composition

100% Polyester

Usable width

min. 140cm

Martindale Test

90 000->100 000

Thread displacement

4.2-4.6 mm WARP / 2.0-2.2 mm WEFT

Tendency to pilling and peeling

4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5



01



05



06




07




08



20



48



55



70

artu

Run again

Uphlostery grade – C2

Grammage m²

380g/m² +/-5%

Composition

94%PES 6%NY

Usable width

min. 140cm

Martindale Test

90000-> 100000

Thread displacement

1,1-1,3 mm WARP / 1,9-2,1 mm WEFT

Tendency to pilling and peeling

4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5



01



02



03



06



11



18



36




48




53



55




61




72




77




80



85



90



99

artu

Tender way

Uphlostery grade – C2

Grammage m²

470g/m² +/-5%

Composition

100%

Usable width

min. 140cm

Martindale Test

80000-90000

Thread displacement

1,4-1,6 mm WARP / 0,9-1,1 mm

Tendency to pilling and peeling


4-5

Fastness to rubbing dry

light-5 / medium-4-5 / dark-4-5

Fastness to rubbing wet

light-5 / medium-4-5 / dark-4-5




01



02




04



37



38




57



63



72




77



80



85



90



97

artu

Concentration

Uphlostery grade – C3

Grammage m²	660g/m ² +/-5%
Composition	100%
Usable width	min. 140cm
Martindale Test	90000->100000
Thread displacement	2,5-2,9 mm WARP / 2,5-2,9 mm WEFT
Tendency to pilling and peeling	4
Fastness to rubbing dry	4-5
Fastness to rubbing wet	4-5




01



21




37




54




59



80




85




90



94



96



99

artu

Good morning

Uphlostery grade – C3

Grammage m²

540g/m² +/-5%

Composition

50%PES 31%VI 12%LI 7%CO

Usable width

min. 140cm

Martindale Test

55000- 70000

Thread displacement

1,9-2,1 mm WARP / 2,0-2,2 mm WEFT

Tendency to pilling and peeling

4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet


4




09



35



59



75



79

artu

Good morning P

Uphlostery grade – C3

Grammage m²

540g/m² +/-5%

Composition

50%PES 31%VI 12%LI 7%CO

Usable width

min. 140cm

Martindale Test

55000- 70000

Thread displacement

1,9-2,1 mm WARP / 2,0-2,2 mm WEFT

Tendency to pilling and peeling


4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet


4




09P




35P



59P



75P



79P

artu


Good night

Uphlostery grade – C3

Grammage m²	550g/m ² +/-5%
Composition	48%PES 29%VI 12%LI 11%CO
Usable width	min. 140cm
Martindale Test	50000- 60000
Thread displacement	2,8-3,2 mm WARP / 3,0-3,4 mm WEFT
Tendency to pilling and peeling	3-4
Fastness to rubbing dry	5
Fastness to rubbing wet	4-5




01




37



70



79




90

artu

One moment

Uphlostery grade – C3



Grammage m²

345g/m² +/-10%

Composition

100% Polyester

Usable width

hmin. 140cm

Martindale Test

47500- 52500

Thread displacement

1.4-1.6 mm WARP / 1.6-1.8 mm WEFT

Tendency to pilling and peeling

3-4

Fastness to rubbing dry

light-5 / medium-4-5 / dark-4-5

Fastness to rubbing wet

light-4-5 / medium-4 / dark-3



02



04



08



09



13




19



35



37




38




48



49



54



59




66




69




70




74




78




80



84



85



87



97



99