

artu

Fabric sample book





C1	Wind	3
	Mossa	4
	Pecos	5
	Pretty	6
	Melody	7
C2	Puente	8
	Magni	9
	Tasos	10
	Now or never	11
	Nube	12
	Baloo	13
C3	Athlon	14
	Grain	15
	Select	16
	Breeze Fusion	17

Table of content

artu

WIND

Uphlostery grade – C1

Grammage m²

230g/m² +/-5%

Composition

100% Polyester

Usable width

min 140 cm

Martindale Test

30000-40000

Thread displacement

2,8-3,2 mm WARP / 2,9-3,3 mm WEFT

Tendency to pilling and peeling


4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4



artu

Mossa

Upholstery grade – C1

Grammage m²

325g/m² +/–10%

Composition

100% Polyester

Usable width

min. 140 cm

Martindale Test

>100000

Thread displacement

3,4–3,8 mm WARP / 2,7–3,3 mm WEFT

Tendency to pilling and peeling


4

Fastness to rubbing dry

5

Fastness to rubbing wet


4–5




artu

Pecos

Upholstery grade – C1




Grammage m ²	300 g/m ²
Composition	88% PES, 12% NY
Usable width	140 cm +/- 2 cm
Martindale Test	75000
Thread displacement	2.8 mm WARP / 2.0 mm WEFT
Tendency to pilling and peeling	3-4
Fastness to rubbing dry	4-5
Fastness to rubbing wet	5



artu

Pretty

Upholstery grade – C1



Grammage m²

450g/m² +/-5%

Composition

100% Polyester

Usable width

min. 140 cm

Martindale Test

60000-100000

Thread displacement

1,7-1,9 mm WARP / 1,9-2,1 mm WEFT

Tendency to pilling and peeling


4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet


4-5



artu

Melody

Upholstery grade – C1



Grammage m²

400 g/m²

Composition

100% PES

Usable width

140 cm +/- 2 cm

Martindale Test

>100000

Thread displacement

2,7 mm WARP / 2,1 mm WEFT

Tendency to pilling and peeling

4

Fastness to rubbing dry

5

Fastness to rubbing wet

5



1



2



3



4



5



6



7



8



9



10



11



12



13



14




15

artu

Puente

Upholstery grade – C2

Grammage m²	500g/m ² +/-5%2
Composition	95%PES 5%CO
Usable width	min. 140 cm
Martindale Test	>100000
Thread displacement	2,6-3,0 mm WARP / 3,7-4,2 mm WEFT
Tendency to pilling and peeling	4
Fastness to rubbing dry	5
Fastness to rubbing wet	4-5



03



06



09



11



16



33



34



35



37



39



41



52



53



69



73



80



92



94

artu

Magni

Upholstery grade – C2

Grammage m²	500g/m ² +/-5%2
Composition	100% PES
Usable width	142 ± 3 cm
Martindale Test	90000
Thread displacement	4,0 mm WARP / 3,0 mm WEFT
Tendency to pilling and peeling	4
Fastness to rubbing dry	5
Fastness to rubbing wet	5



206.01



206.02



206.03



206.04



206.05



206.06



206.07



206.08



206.09



206.10



206.11



206.12



206.13



206.14



206.15



206.16



206.17



206.18

artu

Tasos

Upholstery grade – C2

Grammage m ²	450 g/m ²
Composition	100% PES
Usable width	142 cm +/- 2 cm
Martindale Test	85000
Thread displacement	1,0 mm WARP / 1,0 mm WEFT
Tendency to pilling and peeling	4-5
Fastness to rubbing dry	4-5
Fastness to rubbing wet	4-5



artu

Now or never

Upholstery grade – C2



RECYCLED
POLYESTER

Grammage m²

420g/m² +/-5%

Composition

100% rPES

Usable width

min. 140 cm

Martindale Test

90 000->100 000

Thread displacement

0,5-0,7 mm WARP / 1,1-1,3 mm WEFT

Tendency to pilling and peeling

3-4

Fastness to rubbing dry


light-5 / medium-4-5 / dark-4-5

Fastness to rubbing wet

light-4-5 / medium-5 / dark-4-5



01



02



03



05



06



14



16




18



34



37



38



54



56



61



64



73



77



79



83



92



100

artu

Nube

Upholstery grade – C2

Grammage m²

360 g/m² +/-5%²

Composition

100% Polyester

Usable width

min. 140 cm

Martindale Test

50000-60000

Thread displacement

1,6-2,0 mm WARP / 1,6-2,0 mm WEFT

Tendency to pilling and peeling


4-5

Fastness to rubbing dry


4-5

Fastness to rubbing wet


4-5



01



02



04



08



11




18




23




25



29



38



39



69



78



79



81



84



90



100

artu

Baloo

Upholstery grade – C2

Grammage m²

570g/m² +/-5%

Composition

93% PES, 6% ACR, 1% COT

Usable width

142 ± 3 cm

Martindale Test

>100000

Thread displacement

2 mm WARP / 3 mm

Tendency to pilling and peeling

4-5

Fastness to rubbing dry

5

Fastness to rubbing wet

4-5



2071



2072



2073



2074



2075



2076



2077



2078



2079



2080



2081



2082



2083



2084



2085



2086




2087



2088



2089



2090

artu

Athlon

Uphlostery grade – C3

Grammage m²

750 g/lm

Composition

100% Polyester

Usable width

140 cm

Martindale Test

100000

Tendency to pilling and peeling

5

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5



6500-68252



6500-60140



6500-60141



6500-60167



6500-60900



6500-68251



6500-61140



6500-61194



6500-61246



6500-62119



6500-68169



6500-63115



6500-64221



6500-64246



6500-64247



6500-65118



6500-65134



6500-65135



6500-65136



6500-66140



6500-66225



6500-66226



6500-66227



6500-66228



6500-66229



6500-67120



6500-67121



6500-68253



6500-68254



6500-68255



6500-68256

artu

Grain

Uphlostery grade – C3

Grammage m²

750 g/lm

Composition

100% Polyester

Usable width

140 cm

Martindale Test

100000

Tendency to pilling and peeling

5

Fastness to rubbing dry


4-5

Fastness to rubbing wet

4-5



artu



Select

Uphloster grade – C3

Grammage m²

510 g/lm

Composition

85% New Zealand wool

15% Polyamide

Usable width

140 cm

Martindale Test

100000-200000

Tendency to pilling and peeling

4

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5

artu

Breeze Fusion

Upholstery grade – C3

Grammage m²

590 g/lm

Composition

88% New Zealand wool

12% Polyamide

Usable width

140 cm

Martindale Test

100000

Tendency to pilling and peeling

4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5

