

artu

Outdoor fabric sample book



C1	Sunlight	3
	Patio	4
	Rainbow	5
	Pico	6
C2	Korsyka	7
	Barbados	8
	Portoriko	9
	Sycylia	10
	Teneryfa	11
C3	Levis	12
	Harris	13

Table of content

artu

Sunlight

Upholstery grade – C1

Grammage m²

230 g/m² +/-10%

Composition

100% olefin

Usable width

min. 160cm

Martindale Test

40000-50000

Thread displacement

2,2-2,6 mm WARP / 1,9-2,1 mm WEFT4-5

Tendency to pilling and peeling


4-5

Fastness to rubbing dry

5

Fastness to rubbing wet

5



artu

Patio

Upholstery grade – C1

Grammage m²

Patio 1: 310 g/m² | Patio 2-5: 360 g/m²
| Patio 6-12: 250 g/m²

Composition

100% SDP (Solution Dyed Polyester)150

Usable width

150 cm +/- 2 cm

Martindale Test

>100000 cykli

Thread displacement

2,0 mm WARP / 2,6 mm WEFT

Tendency to pilling and peeling

4

Fastness to rubbing dry


5

Fastness to rubbing wet

5




01



02




03




04



05



06



07




08




09



10



11



12

artu

Rainbow

Upholstery grade – C1

Grammage m²	250 g/m ²
Composition	100% SDP (Solution Dyed Polyester)
Usable width	150 cm +/- 2 cm
Martindale Test	>100 000 cykli
Thread displacement	2.0 mm WARP / 2.6 mm WEFT
Tendency to pilling and peeling	4
Fastness to rubbing dry	5
Fastness to rubbing wet	5




artu

Pico

Upholstery grade – C1

Grammage m ²	450g/m ² +/-5%
Composition	100% olefin
Usable width	min. 140 cm
Martindale Test	40000-50000
Thread displacement	1,9-2,1 mm WARP / 1,7-1,9 mm WEFT4-5
Tendency to pilling and peeling	4
Fastness to rubbing dry	5
Fastness to rubbing wet	5



04



23




34




37



53




58



71



73



77



82



99

artu

Korsyka

Uphlostery grade – C2

Grammage m²	350 g/m ²
Composition	100% olefin
Usable width	140 cm ± 2 cm
Martindale Test	27000
Thread displacement	2,8 mm WARP / 3,7 mm WEFT
Tendency to pilling and peeling	5
Fastness to rubbing dry	4-5
Fastness to rubbing wet	4-5



7111



7112



7113



7114



7115



7116



7117



7118



7119



7120



7121



7122



7123



7124



7125



7126

artu

Barbados

Uphlostery grade – C2

Grammage m²	350 g/m ²
Composition	100% olefin
Usable width	140 cm ± 2 cm
Martindale Test	24000
Thread displacement	2,8 mm WARP / 2,7 mm WEFT
Tendency to pilling and peeling	4-5
Fastness to rubbing dry	4-5
Fastness to rubbing wet	4-5



7251



7252



7253




7254




7255



7256



7357



7258



7259




7260



7261



7262



7263



7264



7265



7266



7267



7268



7269

artu

Portoriko

Upholstery grade – C2

Grammage m²

460 g/m²

Composition

100% olefin

Usable width

140 cm ± 2 cm

Martindale Test

50000

Thread displacement

2,5 mm WARP / 2,5 mm WEFT

Tendency to pilling and peeling

4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet

4-5



7171



7172



7173



7174



7175



7176



7177



7178



7179




7180



7181



7182




7183



7184



7185



7186



7187



7188



7189

artu

Sycylia

Upholstery grade – C2

Grammage m²

450 g/m²

Composition

100% olefin

Usable width

140 cm ± 2 cm

Martindale Test

Category A (56 000)

Thread displacement

2,6 mm WARP / 3,0 mm WEFT

Tendency to pilling and peeling


4-5

Fastness to rubbing dry

4-5

Fastness to rubbing wet


4-5



7201




7202




7203




7204



7205




7206



7207




7208




7209




7210




7211




7212




7213




7214



7215




7216



7217



7218



7219

artu

Teneryfa

Uphlostery grade – C2

Grammage m²	460 g/m ²
Composition	100% olefin
Usable width	140 cm ± 2 cm
Martindale Test	25000
Thread displacement	3,7 mm WARP / 4,4 mm WEFT
Tendency to pilling and peeling	5
Fastness to rubbing dry	4-5
Fastness to rubbing wet	4-5



7141



7142



7143



7144



7145



7146



7147



7148



7149



7150



7151



7152



7153



7154



7155



7156



7157



7158



7159

artu

Lewis

Uphlostery grade – C3

Grammage m ²	417 g/m ² +/- 5%
Composition	100% olefin
Usable width	140 cm ± 2 cm
Martindale Test	40000
Thread displacement	4,4 mm WARP / 4,3 mm WEFT
Tendency to pilling and peeling	4-5
Fastness to rubbing dry	4
Fastness to rubbing wet	4



7541



7542



7543



7544



7545



7546



7547

Harris

Upholstery grade – C3

Grammage m²	416 g/m ² +/- 5%
Composition	100% olefin
Usable width	140 cm ± 2 cm
Martindale Test	20000
Thread displacement	2,4 mm WARP / 3,8 mm WEFT
Tendency to pilling and peeling	4-5
Fastness to rubbing dry	4
Fastness to rubbing wet	4



7521



7522



7523



7524



7525



7526